

# Professional Pro 100

### Interior Latex Pearl 125-00

#### **Technical Information**

Gloss Range

23 - 33 (60° angle)

White untinted

Vehicle Type Vinyl Acrylic Copolymer/Acrylic

Spreading Rate

3.78 liters will cover up to 35 square meters or up to 350 square feet per coat, depending on the porosity and texture of the substrate

% Solids (based on White) By Volume: 17.54

By Weight: 27.93

Weight per 3.78L: 5.01 Kg (including can)

Dry Time

(Based on White under normal conditions)

To Touch: 1 hours
To Recoat: 6 hours
Full Cure: 30 days

Surface Temperature

Minimum: 10 °C or 50 °F Maximum: 32 °C or 90 °F

Storage Temperature

Minimum: 5 °C or 41 °F Maximum: 35 °C or 95 °F

Note: 19L plastic pails stored at high temperatures for prolonged periods may experience skinning

Viscosity	86 – 92 Krebs Units		
Flash Point	N/A		
Container Sizes			
125-00 White		3.7 L	1848-952
		18.5L	1848-951

\*Contact your local municipal office for specific disposal guidelines in your region.\*

## **Features and Benefits**

- ♦ Dries fast
- High hiding
- ♦ Low spatter
- ♦ Washable
- Scrubable
- ♦ Available in white
- Easy soap and water clean up
- ♦ VOC's are < 150g/L White

### **Recommendations**

- ♦ Good for:
  - \* Kitchens
  - \* Bathrooms

### Limitations

- All wood must be properly sealed to prevent tannin bleed through.
- Available in white.
- ◆ Temperature must be 10 °C for a minimum of 48 hours.
- Do not apply in damp conditions or where mildew is present. (remove all traces of mildew)
- May wash with mild detergent after 30 days.

### **Optimal Performance Guidelines**

- Always use premium applicators. Synthetic bristle brush and high quality lint free rollers are recommended. May be sprayed.
- ♦ All surfaces must be clean, dull, dry and free of dust, grease, wax or any other contaminants.
- ♦ Clean surface with T.S.P and rinse
- While applying paint always maintain a wet edge and a liberal uniform film thickness.
- Thinning is not recommended.
- ♦ Always stir thoroughly before and during use.
- Follow label/lid directions for application and primer requirements.