



Features and Benefits

- ◆ Dries fast
- ◆ Interior and Exterior use
- ◆ Tintable to pastel shades
- ◆ Easy soap and water clean up
- ◆ VOC's are ≤ 150g/L-base untinted

Recommendations

- ◆ For Line marking on:
 - * Crosswalks & stop zones
 - * Specialty parking areas
 - * Recreation rooms
 - * Warehouse & factory floors

Limitations

- ◆ Not recommended for Roads and highway application
- ◆ Do not apply to new asphalt for a minimum of 1 year
- ◆ Do not apply in direct sun or when rain imminent
- ◆ Temperature must be 10 °C for a minimum of 48 hours
- ◆ Must be Tinted

Optimal Performance Guidelines

- ◆ Always use premium applicators. Synthetic bristle brush and high quality lint free rollers are recommended. May be sprayed.
- ◆ Fill cracks with Weather Shield Acrylic Crack Filler
- ◆ Clean surface with Weather Shield Concrete & Asphalt Cleaner. Rinse well.
- ◆ Before application lightly dampen surface (not wet). In order to maintain maximum coverage. Critical for warm weather, sunny or windy days.
- ◆ Apply in a THIN uniform coat using brush or roller.
- ◆ Asphalt surface must be in good condition and without exposed aggregate for proper adhesion.
- ◆ Thinning is not recommended.
- ◆ Before painting, make sure that enough paint is purchased and boxed together to ensure a uniform colour. (especially critical for tints)
- ◆ Follow label directions for application.

Technical Information

Gloss Range
< 5 (60 ° angle)

Vehicle Type Acrylic

Spreading Rate

4 liters will cover up to 18-37 square meters or up to 190-390 square feet per coat. Covers approximately 570-1170 linear feet of 4" lines.

% Solids (untinted)

By Volume: 25.54

By Weight: 39.48

Weight per 3.48L: 4.32 Kg including can

Dry Time

(Based on White under normal conditions)

To Touch: 1 hours

Recoat : 6 hours

Full Cure: 30 days

Surface Temperature

Minimum: 10 °C or 50 °F

Maximum: 33 °C or 90 °F

Storage Temperature

Minimum: 5 °C or 41 °F

Maximum: 35 °C or 95 °F

Note: 19L plastic pails stored at high temperatures for prolonged periods may experience skinning

Viscosity 78 – 83 Krebs Units

Flash Point N/A

Container Sizes

210-04 – Med. Tint Base	3.48L	1829-632
	17.4L	1829-633

Contact your local municipal office for specific disposal guidelines in your region.