



# Professional Pro 300

## Interior Latex Ultra Flat

### 305-00

#### Features and Benefits

- ◆ Dries fast
- ◆ High hiding
- ◆ Low spatter
- ◆ Interior use
- ◆ Available in white and tintable in pastel shades
- ◆ Easy soap and water clean up
- ◆ Flat sheen hides surface imperfections
- ◆ Superior Touch-up
- ◆ VOC's are ≤ 50 g/L- White
- ◆ MPI – 53 - ( 305-00 only )

#### Recommendations

- ◆ Good for walls or ceilings in:
  - \* Bedrooms
  - \* Living rooms
  - \* Dining rooms

#### Limitations

- ◆ Not recommended for trim, woodwork or metal.
- ◆ All wood must be properly sealed to prevent tannin bleed through.
- ◆ Temperature must be 10 °C for a minimum of 48 hours.
- ◆ High humidity and cool temperatures may increase dry time.
- ◆ Do not clean with abrasive cleaners.
- ◆ Do not apply in damp conditions or where mildew is present. (remove all traces of mildew)
- ◆ May wash with a mild detergent after 30 days

#### Optimal Performance Guidelines

- ◆ Always use premium applicators. Synthetic bristle brush and high quality lint free rollers are recommended. May be sprayed.
- ◆ All surfaces must be clean, dull, dry and free of dust, grease, wax or any other contaminants.
- ◆ Clean surfaces with T.S.P. and rinse well
- ◆ While applying paint always maintain a wet edge and a liberal uniform film thickness.
- ◆ Before painting make sure that enough paint is purchased and boxed together to ensure a uniform colour. (especially critical for tints)
- ◆ Rusty nail heads must be sealed with an alkyl.
- ◆ Follow label/lid directions for application and primer requirements.

#### Technical Information

Gloss Range  
0 - 3 (60 ° angle)  
White untinted

---

Vehicle Type          Vinyl Acrylic Copolymer

---

Spreading Rate  
4 litre will cover up to 40 square meters or up to 400 square feet per coat, depending on the porosity and texture of the substrate.

---

% Solids :	Ultra Flat White	Ceiling flat
By Volume:	28.10	29.58
By Weight:	46.26	46.28

Weight per 3.78 L: 5.37 Kg including can

---

Dry Time  
(Based on White under normal conditions)

To Touch:	1 hour
To Recoat:	6 hours
Full Cure:	30 days

---

Surface Temperature

Minimum:	10 °C	or	50 °F
Maximum:	32 °C	or	90 °F

---

Storage Temperature

Minimum:	5 °C	or	41 °F
Maximum:	35 °C	or	95 °F

Note: 19L plastic pails stored at high temperatures for prolonged periods may experience skinning

---

Viscosity 95 –102 Krebs Units

---

Flash Point          N/A

---

Container Sizes

305-00 – White	3.64 L	1825-535
	18.2 L	1825-536

300-50- Ceiling Flat	7.5L	1828-531
----------------------	------	----------

\*Contact your local municipal office for specific disposal guidelines in your region.\*