



## INT. PRO 300 PEARL 325-00

### Description

PRO 300 Interior Latex Pearl Paint was developed to perform optimally through the combination of resin and proprietary formulation. A professional line that offers exceptional durability, ease of application, and excellent coverage.

### Recommended Substrates

Gypsum Wallboard / Drywall – Plaster (Primed) – Trim

### Tinting and Base Information

325-00 White – Pastels - Tintable

\*Can be tinted. Refer to the formula book or colour matching system for colour formulas and tinting instructions. Some tints, drastic colour changes, or porous substrate may require a primer coat or more than two coats to achieve a uniform finish.

### Features

Professional Grade  
Scrubable and Washable  
Latex Formulation  
Excellent Flow and Leveling  
Home Owners Guarantee

### Benefits

Low Splattering  
Smooth application promotes exceptional hiding and coverage  
Easy soap and water clean-up  
Helps minimize surface imperfections

### Regulatory Conformance and Approvals

Meets stringent VOC regulation -  $\leq 50$  g/L (based on 325-00)

### Technical Data

**Vehicle Type:** Vinyl Acrylic Copolymer

**Gloss Range:** 23-33 (60° angle) based on 325-00

**Spread Rate:** Up to 40m<sup>2</sup> or 400ft<sup>2</sup> per gallon on smooth and non-porous surfaces. Spread Rate does not include loss due to surface irregularities, surface porosity, and application method.

**Volume Solids\*:** 32% based on 325-00

**Weight Solids\*:** 46% based on 325-00

\*Weight per 3.64L – 5.06kg including can

**Drying Time: @ 25°C; 50% Relative Humidity**

To Touch – 1 hours  
To Recoat – 6 hours  
To Full Cure – 30 days

*Drying times will vary depending on ambient temperature, humidity, film build, colour, and air movement.*

**Surface Temperature:**

Material – 10°C (50°F) to 32° (90°F)  
Ambient - 10°C (50°F) to 32° (90°F)  
Substrate - 10°C (50°F) to 32° (90°F)

*Materials stored at elevated temperatures for prolonged periods may experience skinning.*

**Viscosity:** 94-100 Krebs Units @ 25°C

**Flash Point:** N/A

**Disposal:** Contact your local environmental regulatory office or your municipality for specific guidelines

### Container Sizes:

325-00 3.64 L 1828-767 18.2 L 1828-776

### General Preparatory Steps and Application Info

- Surface must be clean, dull, and dry
- Remove all loose and peeling paint, dirt, mildew, grease, stains, and any other surface contamination. Putty all nail holes, repair all cracks and open seams.
- Sand all glossy finishes (alkyd paints), rough, and patched surfaces.
- For severe stains, water marks, tannins, and other challenging surfaces (alkyd paints) use an appropriate BT specialty primer.
- Follow label directives for application and primer requirement. Consult your local Paint Department.

**New Gypsum Wallboard / Drywall:** Ensure surface is sanded smooth and cleaned prior to painting. Prime the surface to ensure excellent adhesion and enamel hold-out. Smoothness of surface and quality drywall finish is essential if the paint is used as is.

**Painted Gypsum Wallboard / Drywall:** Ensure the surface is repaired, sanded, cleaned with TSP plus and rinsed well prior to painting.

**Plaster:** Allow new surface to cure for 30 days and prime. If previously painted, proceed with 325-00.

**Trim:** Degrease (if applicable), sand, and clean the surface prior to priming with appropriate primer. Please consult with your local Paint Department.

**Soluble Stains:** Prime with a BT specialty primer or alkyd primer.

- Allow a minimum of 30 days to cure.
- Always maintain a wet edge and a liberal uniform film thickness. Do not back roll.
- Only work 4 feet ahead if cutting-in to avoid picture framing.
- Always use premium applicators. Ensure adequate ventilation during application (spring and winter months are not ideal).
- Stir thoroughly before and occasionally during use.
- If using more than one can of the same, intermix to ensure uniform finish.

**Application Equipment:** Apply with a high-quality brush, roller, paint pad, or sprayer.

Sprayer – 0.015"-0.021" nozzle tip at manufacture PSI recommendation.

Brush – Synthetic Bristle.

Roller – 5mm – 10mm nap cover.

**Thinning:** Water - Not necessary but no more than 10%-12% of volume.