



SIGNATURE SERIES

Int/Ext Oil Primer Sealer

59-20

Features and Benefits

- ◆ Interior and Exterior
- ◆ Tintable and Sandable
- ◆ For use on new or previously painted surfaces
- ◆ Blocks most stains
- ◆ Resists tannic bleed through
- ◆ Home Owner's Guarantee
- ◆ VOC < 350 ° g/L

Recommendations

- ◆ Good for
 - * Wood , Doors and trim
 - * Graffiti, ball point pen, pencil, water based marker, lipstick
 - * Stucco and blown ceilings
 - * Nicotine & smoke stains
 - * Glossy surfaces

Limitations

- ◆ Clean up with Home Paint Thinner.
- ◆ Additional dry time may be required for cool temp or high humidity.
- ◆ Since this is a true Alkyd product, Yellowing of film will occur over time and lack of light
- ◆ Do not paint in extreme heat, direct sun or when rain is imminent.
- ◆ All wood must be properly sealed to prevent tannin bleed through. Unstained surfaces may be top coated in 8 hours.
- ◆ For optimum stain blocking apply two coats- 24 hours between each coat of primer. Then topcoat after 24 hours. If stain still bleeds through 2nd coat, apply a 3rd coat of primer. Let dry 48 hours before top coating.
- ◆ Must be top-coated.
- ◆ Temperature must be 10 °C for a minimum of 48 hours.
- ◆ Cross ventilation and adequate air exchange will help reduce dry time and minimize odors.
- ◆ Keep away from open spark and flame.
- ◆ Submerge paint/solvent soaked rags in water to prevent spontaneous combustion.
- ◆ Do not apply in damp conditions or where mildew is present. (remove all traces of mildew)

Optimal Performance Guidelines

- ◆ Always use premium applicators. Pure bristle brush and high quality lint free rollers are recommended. May be sprayed.
- ◆ Sand new wood to remove mill glaze prior to priming.
- ◆ While applying paint always maintain a wet edge and a liberal uniform film thickness.
- ◆ All surfaces must be clean, dull, dry and free of dust, grease, wax or any other contaminants.
- ◆ Follow label directions for application

Technical Information

Gloss Range
< 17 (60 ° angle)

Vehicle Type Alkyd

Spreading Rate
1 litre will cover up to 10 square meters or up to 100 square feet per coat, depending on the porosity and texture of the substrate.

% Solids (based on White)
53.49% by Volume:
74.28% by Weight:
Weight per 3.64L: Kg including can

Film Thickness
(according to maximum spreading rate)

Dry:	1.5 mils @	sq. ft. per 3.64 L
Wet:	3.8 mils @	sq. ft. per 3.64 L

Dry Time
(Based on White)

To Touch:	4 hours
To Recoat:	8 hours for unstained surface, 24 hours for optimum stain blocking.

Surface Temperature

Minimum:	10 °C	or	50 °F
Maximum:	32 °C	or	90 °F

Storage Temperature

Minimum:	5 °C	or	41 °F
Maximum:	35 °C	or	95 °F

Note: 19L pails stored at high temperatures for prolonged periods may experience skinning

Viscosity; 89 - 95 Kres Units

Flash Point 42 °C

Container Sizes

59-20 –tintable white	911 mL	1831-870
	3.64 L	1831-871
	18.2 L	1831-872

Contact your local municipal office for specific disposal guidelines in your region.