



Signature Series Latex Drywall Primer Sealer 80-00

Features and Benefits

- ◆ Dries fast
- ◆ Sandable
- ◆ High hiding
- ◆ Excellent sealing properties
- ◆ Spatter resistant
- ◆ Easy soap and water clean up
- ◆ Home Owner's Guarantee
- ◆ VOC's are <50 g/L - white

Recommendations

- ◆ Good for:
 - * Drywall
 - * Gypsum board
 - * Cured plaster
 - * Multiple coats of flat finish (porous surfaces)

Limitations

- ◆ For interior use only.
- ◆ Not recommended for bare woods.
- ◆ All wood must be properly sealed to prevent tannin bleed through.
- ◆ When topcoating any alkyd paint with sheen, prime with 59-20 or 80-10
- ◆ Temperature must be 10 °C for a minimum of 48 hours.
- ◆ White only.
- ◆ Do not apply in damp conditions or where mildew is present. (remove all traces of mildew)
- ◆ Must be top-coated.

Optimal Performance Guidelines

- ◆ Always use premium applicators. Synthetic bristle brush and high quality lint free rollers are recommended. May be sprayed.
- ◆ While applying paint, always maintain a wet edge and a liberal uniform film thickness.
- ◆ All surfaces must be clean, dull, dry, and free of dust, grease, wax, or any other contaminants.
- ◆ Follow label/lid directions for application.

Technical Information

Gloss Range
≤ 5 (60 ° angle)

Vehicle Type Vinyl Acrylic Copolymer

Spreading Rate

4 litres will cover up to 40 square meters or up to 400 square feet per coat, depending on the porosity and texture of the substrate.

% Solids

By Volume: 34.7

By Weight: 54.2

Weight per 3.78 L: 5.273 Kg including can

Dry Time

To Touch: 1 hour

To Recoat: 4 hours

Full Cure: 30 days

Note: Additional dry time may be required for high humidity or cool temperatures

Surface Temperature

Minimum: 10 °C or 50 °F

Maximum: 32 °C or 90 °F

Storage Temperature

Minimum: 5 °C or 41 °F

Maximum: 35 °C or 95 °F

Note: 19L plastic pails stored at high temperatures for prolonged periods may experience skinning

Viscosity 95 – 103 Krebs Units

Flash Point N/A

Container Sizes

80-00 - White 946 mL 1850-116

3.78 L 1850-615

18.9 L 1850-624

Contact your local municipal office for specific disposal guidelines in your region.