

Description

Beauti-Tone Interior and Exterior is a premium alkyd spray paint developed to perform optimally through the combination of resin and proprietary formulation. The fluorescent aerosol offers remarkable adhesion, and smooth finish for a multitude of surfaces.

Recommended Substrates

Metal – Wood – Fiberglass - Plastic & More

Product Information

A127-JO* Jamaica Orange
A127-SO* Sunset Orange
A127-HP* Hot Pink
A127-TG* Turf Green

*Drastic colour changes, or porous substrate may require more than two coats to achieve a uniform finish and colour.

Features

Premium Spray Paint
Weather resistant
Comfort Spray Tip
Excellent Adhesion
Acrylic Lacquer Formulation
Fast Drying
Home Owners Guarantee

Benefits

Quick dry
Excellent long-term performance and durable finish

Regulatory Conformance and Approvals

Not Applicable

Technical Data

Vehicle Type: Acrylic Lacquer – Clean up with Home Paint Thinner

Gloss Range: <10 (60° angle) based on a A127-HP

Spread Rate: Up to 1.3m² or 14 ft² per 340g on smooth and non-porous surfaces. Spread Rate do not include loss due to surface irregularities, surface porosity, material loss, and application method.

Volume Solids*: 11% based on A127-HP

Weight Solids*: 15% based on A127-HP

*Weight per 315g can – 0.45kg including can and cap

Drying Time: @ 21°C; 50% Relative Humidity

To Touch – 30 minutes

To Recoat – Within 1 hour or wait 72 hours

To Full Cure – 72+ hours

Drying times will vary depending on ambient temperature, humidity, film build, colour, and air movement.

Surface Temperature:

Material – 15°C (60°F) to 30° (85°F)

Ambient - 15°C (60°F) to 30° (85°F)

Substrate - 15°C (60°F) to 30° (85°F)

Storage of material at elevated temperatures for prolonged periods may affect product and integrity of packaging.

Viscosity: N/A Krebs Units @ 25°C

Flash Point: Flammable

Disposal: Contact your local environmental regulatory office or your municipality for specific guidelines

Container Sizes:

A127-JO – Jamaica Orange	315 g	1740-254
A127-SO – Sunset Orange	315 g	1740-263
A127-HP – Hot Pink	315 g	1740-245
A127-TG – Turf Green	315 g	1740-227

General Preparatory Steps and Application Info

- Surface must be clean, dull and dry.
- Surface must be in sound condition.
- Remove all loose and peeling paint, dirt, mildew, grease, stains, and any other surface contamination with appropriate cleaner.
- Sand all glossy (alkyd paints) and rough surfaces.
- Shake well for 1 minute before and during use.
- Hold can upright 8-12" from the surface.
- Spray light coats in a steady back and forth motion while overlapping each pass (this will avoid runs). Do not stop spraying until the piece is coated and repeat. Apply 2-3 light coats within a few minutes.
- Ideal dry and recoat times are based on 21° @ 50% relative humidity.
- Follow label directives for application and primer requirement. Consult your local Paint Department.
- Cross ventilation and adequate air exchange will help reduce dry time and minimize odours.
- Any solvent soaked tools or rags must be submerged in water to avoid spontaneous combustion. Important to extinguish any pilot light if using in proximity.**

Polyethylene (Plastic) / PVC: Certain plastic components may hinder paint adhesion. Apply a test spot first. After 4-5 days, maximum adhesion will be reached.

Clean-up and Storage: Invert and spray to clean nozzle after use. Clean the nozzle tip with Home paint thinner.

Application Equipment: N/A

Thinning: N/A