

Description

Beauti-Tone Interior and Exterior is a premium alkyd spray paint developed to perform optimally through the combination of resin and proprietary formulation. The High Heat aerosol renews and protects metal surfaces subjected to heat up to 650 °C (1200 °F).

Recommended Substrates

Exterior Barbecue, Wood Stoves, Fire Pits, Fireplace Screens, & More
(No contact with direct flame or in direct contact with food)

Product Information

A135-10* Black

**Porous substrate may require more than two coats to achieve a uniform finish and colour.*

Features

Premium Spray Paint
Rust Inhibitor Qualities
Comfort Spray Tip
Self-Priming
Alkyd Formulation
Home Owners Guarantee

Benefits

Excellent Adhesion
Excellent Hiding
Excellent long-term performance and durable finish

Regulatory Conformance and Approvals

Not Applicable

Technical Data

Vehicle Type: Alkyd – Clean up with Acetone

Gloss Range: 0-3 (60° angle) based on a A135-10

Spread Rate: Up to 1.3m² or 14 ft² per 340g on smooth and non-porous surfaces. Spread Rate does not include loss due to surface irregularities, surface porosity, material loss, and application method.

Volume Solids*: 6.3% based on A135-10

Weight Solids*: 16.4% based on A135-10

*Weight per 340g can – 0.48kg including can and cap

Drying Time: @ 21°C; 50% Relative Humidity

To Touch – 30 minutes

To Recoat – Within 1 hour or wait 72 hours

To Full Cure – 72+ hours

Drying times will vary depending on ambient temperature, humidity, film build, colour, and air movement.

Surface Temperature:

Material – 15°C (60°F) to 30° (85°F)

Ambient - 15°C (60°F) to 30° (85°F)

Substrate - 15°C (60°F) to 30° (85°F)

Storage of material at elevated temperatures for prolonged periods may affect product and integrity of packaging.

Viscosity: N/A Krebs Units @ 25°C

Flash Point: Flammable

Disposal: Contact your local environmental regulatory office or your municipality for specific guidelines

Container Sizes:

A135-10 – Black 315 g 1820-454

General Preparatory Steps and Application Info

- Surface must be clean, dull, and dry.
 - Surface must be in sound condition.
 - Remove all loose or flaking rust.
 - Remove all loose and peeling paint, dirt, mildew, grease, stains, and any other surface contamination with appropriate cleaner.
 - Sand all glossy (alkyd paints) and rough surfaces.
 - Shake well for 1 minute before and during use.
 - Hold can upright 8-12" from the surface.
 - Spray light coats in a steady back and forth motion while overlapping each pass (this will avoid runs). Do not stop spraying until the piece is coated and repeat. Apply 2-3 light coats within a few minutes.
 - Ideal dry and recoat times are based on 21° @ 50% relative humidity.
 - Follow label directives for application and primer requirement. Consult your local Paint Department.
 - Can be used on certain automotive parts – suggest consulting with automotive parts retailer.
 - Cross ventilation and adequate air exchange will help reduce dry time and minimize odours.
 - Any solvent soaked tools or rags must be submerged in water to avoid spontaneous combustion. Important to extinguish any pilot light if using in proximity.**
- Clean-up and Storage:** Invert and spray to clean nozzle after use. Clean the nozzle tip with Acetone.

Application Equipment: N/A

Thinning: N/A