

Description

Beauti-Tone Interior and Exterior is a premium alkyd spray paint developed to perform optimally through the combination of resin and proprietary formulation. The enamel flat offers remarkable adhesion, smooth finish, and Xtended coverage for a multitude of surfaces.

Recommended Substrates

Metal – Wood – Fiberglass - Plastic & More

Product Information

A92-00* White

A92-10* Black

*Drastic colour changes, or porous substrate may require a primer coat or more than two coats to achieve a uniform finish.

Features

Premium Spray Paint
Xtended Coverage
Comfort Spray Tip
Excellent Adhesion
Alkyd Formulation
Fast Drying
Home Owners Guarantee

Benefits

Covers surfaces in less passes.
Smooth spray application that promotes exceptional hiding and coverage.
Excellent long-term performance and durable finish.

Regulatory Conformance and Approvals

Not Applicable

Technical Data

Vehicle Type: Alkyd – Clean up with Acetone

Gloss Range: <10 (60° angle) based on a A92-00

Spread Rate: Up to 1.3m² or 14 ft² per 340g on smooth and non-porous surfaces. Spread Rate does not include loss due to surface irregularities, surface porosity, material loss, and application method.

Volume Solids*: 9.8% based on A92-00

Weight Solids*: 21.5% based on A92-00

*Weight per 340g can – 0.45kg including can and cap

Drying Time: @ 21°C; 50% Relative Humidity

To Touch – 30 minutes

To Recoat – Within 1 hour or wait 72 hours

To Full Cure – 72+ hours

Drying times will vary depending on ambient temperature, humidity, film build, colour, and air movement.

Material – 15°C (60°F) to 30° (85°F)

Ambient - 15°C (60°F) to 30° (85°F)

Substrate - 15°C (60°F) to 30° (85°F)

Storage of material at elevated temperatures for prolonged periods may affect product and integrity of packaging.

Viscosity: N/A Krebs Units @ 25°C

Flash Point: Flammable

Disposal: Contact your local environmental regulatory office or your municipality for specific guidelines

Container Sizes:

A92-00 - White 340 g 1720-203

A92-10 - Black 340 g 1720-204

General Preparatory Steps and Application Info

- Surface must be clean, dull and dry.
- Surface must be in sound condition.
- Remove all loose and peeling paint, dirt, mildew, grease, stains, and any other surface contamination with appropriate cleaner.
- Sand all glossy (alkyd paints) and rough surfaces.
- Shake well for 1 minute before and during use.
- Hold can upright 8-12" from the surface.
- Spray light coats in a steady back and forth motion while overlapping each pass (this will avoid runs). Do not stop spraying until the piece is coated and repeat. Apply 2-3 light coats within a few minutes.
- Ideal dry and recoat times are based on 21° @ 50% relative humidity.
- Follow label directives for application and primer requirement. Consult your local Paint Department.
- Cross ventilation and adequate air exchange will help reduce dry time and minimize odours.
- Any solvent soaked tools or rags must be submerged in water to avoid spontaneous combustion. Important to extinguish any pilot light if using in proximity.**
- Polyethylene (Plastic) / PVC:** Certain plastic components may hinder paint adhesion. Apply a test spot first. After 4-5 days, maximum adhesion will be reached.
- Clean-up and Storage:** Invert and spray to clean nozzle after use. Clean the nozzle tip with acetone.
- Cross ventilation and adequate air exchange will help reduce dry time and minimize odours.

Application Equipment: N/A

Thinning: N/A

Surface Temperature: