

Description

Beauti-Tone Interior and Exterior is a premium lacquer spray paint developed to perform optimally through the combination of resin and proprietary formulation. The lacquer aerosol offers remarkable adhesion, and smooth finish for a multitude of surfaces.

Recommended Substrates

Metal – Wood – Fiberglass - Plastic & More

Product Information

A97-03* Clear
 A97-10* Gloss Black
 A97-00* Super White
 A97-AU* Gold
 A97-CU* Copper
 A97-AG* Silver
 A97-BS* Brass

*Drastic colour changes, or porous substrate may require more than two coats to achieve a uniform finish and colour.

Features

Premium Spray Paint
 Weather Resistant
 Comfort Spray Tip
 Excellent Adhesion
 Acrylic Lacquer formulation based on modified acrylic polymer
 Fast Drying
 Home Owners Guarantee

Benefits

Quick dry.
 Not a Nitrocellulose base product.
 Excellent long-term performance and durable finish.

Regulatory Conformance and Approvals

Not Applicable

Technical Data

Vehicle Type: Acrylic Lacquer – Clean up with Acetone

Gloss Range: <10 (60° angle) based on a A97-00

Spread Rate: Up to 1.3m² or 14 ft² per 340g on smooth and non-porous surfaces. Spread Rate does not include loss due to surface irregularities, surface porosity, material loss, and application method.

Volume Solids*: 10% based on A97-00

Weight Solids*: 21% based on A97-00

*Weight per 315g can – 0.48kg including can and cap

Drying Time: @ 21°C; 50% Relative Humidity

To Touch – 30 minutes

To Recoat – Within 1 hour or wait 72 hours

To Full Cure – 72+ hours

Drying times will vary depending on ambient temperature, humidity, film build, colour, and air movement.

Surface Temperature:

Material – 15°C (60°F) to 30° (85°F)

Ambient - 15°C (60°F) to 30° (85°F)

Substrate - 15°C (60°F) to 30° (85°F)

Storage of material at elevated temperatures for prolonged periods may affect product and integrity of packaging.

Viscosity: N/A Krebs Units @ 25°C

Flash Point: Flammable

Disposal: Contact your local environmental regulatory office or your municipality for specific guidelines

Container Sizes:

A97-03 – Clear	315 g	1730-103
A97-10 – Gloss Black	315 g	1730-112
A97-00 – Super White	315 g	1730-121
A97-AU – Gold	315 g	1730-130
A97-CU – Copper	315 g	1730-158
A97-AG – Silver	315 g	1730-176
A97-BS – Brass	315 g	1730-185

General Preparatory Steps and Application Info

- Surface must be clean, dull, and dry.
- Surface must be in sound condition.
- Remove all loose and peeling paint, dirt, mildew, grease, stains, and any other surface contamination with appropriate cleaner.
- Sand all glossy (alkyd paints) and rough surfaces.
- Shake well for 1 minute before and during use.
- Hold can upright 8-12" from the surface.
- Spray light coats in a steady back and forth motion while overlapping each pass (this will avoid runs). Do not stop spraying until the piece is coated and repeat. Apply 2-3 light coats within a few minutes.
- Ideal dry and recoat times are based on 21° @ 50% relative humidity.
- Follow label directives for application and primer requirement. Consult your local Paint Department.
- Cross ventilation and adequate air exchange will help reduce dry time and minimize odours.
- Any solvent soaked tools or rags must be submerged in water to avoid spontaneous combustion. Important to extinguish any pilot light if using in proximity.**

Polyethylene (Plastic) / PVC: Certain plastic components may hinder paint adhesion. Apply a test spot first. After 4-5 days, maximum adhesion will be reached.

Clean-up and Storage: Invert and spray to clean nozzle after use. Clean the nozzle tip with acetone.

Application Equipment: N/A

Thinning: N/A