



# SAFE ETCH C17-20

## Description

Natura Safe Etch was developed to perform optimally through the combination of proprietary formulation and advancement. A safe choice for etching masonry exterior and interior surfaces.

## Recommended Substrates

Masonry Surfaces – Concrete, Stone, and Brick

## Tinting and Base Information

N/A

## Features

Ready to Use  
Safe Etching Alternative to Muriatic Acid  
Acid Salts Formulation  
Home Owners Guarantee

## Benefits

Roughens-up smooth masonry  
Non-Corrosive  
Non-Hazardous  
Organic and Safe

## Regulatory Conformance and Approvals

N/A

## Technical Data

**Vehicle Type:** N/A

**Gloss Range:** N/A

**Spread Rate:** N/A

**Wet Film Thickness:** N/A

**Dry Film Thickness:** N/A

*Spread Rate do not include loss due to surface irregularities, surface porosity, and application method*

**Volume Solids\*:** N/A

**Weight Solids\*:** N/A

\*N/A

**Drying Time:** @ 25°C; 50% Relative Humidity

To Touch – N/A

To Recoat – N/A

To Full Cure – N/A

*Drying times will vary depending on ambient temperature, humidity, film build, colour, and air movement.*

**Colour:** Clear

**Fragrance:** Low Odour

**pH:** 1.08

**Specific Gravity:** 1.03

**Surface Temperature:**

Material – 10°C (50°F) to 32° (90°F)

Ambient - 10°C (50°F) to 32° (90°F)

Substrate - 10°C (50°F) to 32° (90°F)

*Storage of material at elevated temperatures for prolonged periods may experience skinning.*

**Viscosity:** N/A

**Flash Point:** N/A

**Disposal:** Contact your local environmental regulatory office or your municipality for specific guidelines

**Container Sizes:**

C17-20 4L 1620R850

## General Preparatory Steps and Application Info

-Ready to Use formula

-Dampen surface to be etched.

-Work in manageable sections (10'X10') at a time.

-Apply Safe Etch onto damp surface, scrub with a stiff bristle brush until foaming action stops.

-Typical etching time is 10-20 minutes.

-Etched surface should feel like 150 medium grit sandpaper.

-Do not allow Safe Etch to dry on the surface.

-Rinse the product off thoroughly with water.

-Power trowled surfaces might be too smooth or glossy for the Safe Etch to work effectively. In some instances, the above needs to be repeated. Under some circumstances, a muriatic acid mixture is necessary. Consult your local Paint Department.

-Do not mix with other products or cleaners.

-Please take extra precaution near and around the project to protect foliage, metal, and glass.

-Follow label directives for application requirement.

**Application Equipment:** Apply with a brush or garden sprayer.

**Thinning:** N/A