



## EXT. END CUT SEALER C210-45

### Description

End Cut is a quality sealer that protects against moisture damage and harmful effects of the sun. This deep penetrating, two coat application protects your pressure treated substrates. Ideal for our Canadian Climate.

### Recommended Substrates

For above ground applications – wood substrates

### Tinting and Base Information

MicroPro Sienna™ Colour

### Features

Exterior  
Advance Water-Based Hybrid Formulation  
Sealing End Cuts  
Home Owner's Guarantee

### Benefits

Outstanding Protective Finish  
Deep Penetrating Finish  
Easy soap and water clean-up

### Regulatory Conformance and Approvals

N/A

### Technical Data

**Vehicle Type:** Water-Based Hybrid

**Gloss Range:** Low Gloss (Not Flat)

**Spread Rate:** Up to 14-28m<sup>2</sup> or 140-280ft<sup>2</sup> per gallon on smooth and non-porous surfaces.

**Wet Film Thickness:** N/A

**Dry Film Thickness:** N/A

*Spread Rate do not include loss due to surface irregularities, surface porosity, and application method*

**Volume Solids\*:** N/A

**Weight Solids\*:** 14.000%

\*Weight per N/A

**Drying Time:** @ 25°C; 50% Relative Humidity

To Touch – 1-2 hours

To Recoat – 1 hour

To Full Cure – 24 hours

*Drying times will vary depending on ambient temperature, humidity, film build, colour, and air movement.*

**Colour:** Brown tone – like MicroPro Sienna™

**Fragrance:** Mild Oil

**Specific Gravity:** 1.019

**Surface Temperature:**

Material – 10°C (50°F) to 32° (90°F)

Ambient - 10°C (50°F) to 32° (90°F)

Substrate - 10°C (50°F) to 32° (90°F)

*Storage of material at elevated temperatures for prolonged periods may experience skinning.*

**Viscosity:** N/A

**Flash Point:** N/A

**Disposal:** Contact your local environmental regulatory office or your municipality for specific guidelines

**Container Sizes:**

C210-45 950ML 1874R954 3.78L 1874R955

**General Preparatory Steps and Application Info**

-Surface must be clean, dull and dry

-Remove all loose and peeling material, dirt, mildew, glue, grease, stains, and any other surface contamination. Remove all traces of mildew.

If the surface beads or sheds water, the coating needs to be removed and thoroughly prepped prior to protecting.

**-TWO COAT APPLICATION.**

-If unsure, apply a small test patch to confirm performance and degree of application.

-Do not use below grade.

-Do not mix with other coatings.

-Do not apply in direct sun or if rain is imminent (within 24 hours).

-Follow label directives for application requirement. Consult your local Paint Department.

-Once sealed, coating will be slippery under wet or icy conditions.

-Stir thoroughly before and occasionally during use.

-If using more than one can of the same, intermix to ensure uniform finish.

**New Pressure Treated Wood:** Ensure the moisture in wood is below 15%. Apply 2 coats of C210-45. Depending on use, a maintenance coat is needed every 48-72 months.

**Application Equipment:** Apply with a high-quality brush, roller, paint pad, or sprayer. Sprayer – 0.015"-0.021" nozzle tip at manufacture PSI recommendation. Brush – Polyester / Nylon. Roller – 10mm – 15mm nap cover.

**Thinning:** N/A